

**BAUXITE ROUND KILN**

ANALYSIS	TYPICAL %	GUARANTEED
Al <sub>2</sub> O <sub>3</sub>	89.25%	88.00% Min
SiO <sub>2</sub>	5.00%	6.00% Max
Fe <sub>2</sub> O <sub>3</sub>	1.53%	1.80% Max
TiO <sub>2</sub>	3.61%	4.00% Max
K <sub>2</sub> O + Na <sub>2</sub> O	0.20%	0.30% Max
CaO + MgO	0.30%	0.45% Max
PHYSICAL PROPERTIES		
Density	3.30 gr/cm <sup>3</sup>	0.25 gr/cm <sup>3</sup> Min
Moisture	Lump 0.40%	Mesh 0.15%
PACKING		
20 kg per carton		

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose.