

RANEBOW YELLOW OXIDE

ANALYSIS		TYPICAL %
Fe ₂ O ₃		0.95%
CaCO ₃		54.69%
MgCO ₃		42.98%
Al ₂ O ₃		0.9%
PYSICAL PROPERTIES		
Particle Size		325 BS mesh
Oil Absorption		18 - 22ml/100gm
Matter Soluble in Water		0.57% max.
Light Fastness		Good
Heat Stability		Good
Resistance to Acid/Alkali		Good
APPLICATION		
Repacking		
Cement		

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose.