



INDEPENDENT MINERAL DISTRIBUTORS (Pty) Ltd

SUPPLIERS OF INDUSTRIAL MINERALS & BASE METALS

Product Data Sheet

BORIC ACID T

Analysis	Typical %	Min.	Max.
Ba ₂ O ₃	56.0 %	56.0	
CL	120 %	100	300
SO ₄	450	300	1 000
Ca	80	60	150
Fe	10	5	20
Moisture	1 000	500	1500
Purity	99.5	99.5	

Physical Properties

Screen - Typical	Retained on 50 mesh	7 %
	Retained on 100 mesh	54%
	Retained on 200 mesh	33%
	Passing 200 mesh	6 %

Packing

25 kg bags or 1 Mt Bulk bags

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose

IMD (Pty) Ltd

4 arlington road, bryanston, 2191, gauteng, south africa t: (011) 706-0322 f (011) 463-2475
info@imdza.com www.imdza.com